



ACF GRANITE AND POOL

Fast Setting Dry Set Marble and granite Adhesive Mortar

Description

ACF GRANITE AND POOL is a specially blended mortar with chemical additives which produce an excellent, fast setting, high strength dry-set mortar. **ACF GRANITE AND POOL** enables the contractor to set tile and grout within two hours so that he will have a finished installation which can be open to foot traffic in 24 hours.

ACF GRANITE AND POOL is used as a bonding adhesive for marbles, granites and ceramic tiles. **ACF GRANITE AND POOL** has excellent water and impact resistance, is water cleanable, non-flammable, good for exterior work. **ACF GRANITE AND POOL** mortar is not affected by prolonged contact with water, but does not form a waterproof barrier. **ACF GRANITE AND POOL** provides a permanent installation with higher bond strength, and lower material and labor cost than conventional Portland cement mortar beds.

Characteristics

Texture	Powder consist of cement, graded sand, organic and inorganic chemicals	
Tensile Adhesion as per EN 1348-clause 8.2	Requirement ≥ 0.5 N/mm ²	Typical value 0.75 – 1.00 N/mm ²

Application

- For exterior and interior walls and floor
- Used as bonding adhesive for Marbles, granites and ceramics

Advantages

- Pre-packed product requiring only direct mixing at site
- Ideal for vertical / horizontal applications
- Quick fixing, reduces labour costs
- Can be used in the interior and exterior of buildings
- High strength mortar
- Excellent grab during open time



Application Methodology

- Ensure that tiling surface is clean, dry, structurally sound, free of all grease, oil, dirt, dust, curing compounds, sealer, coatings, efflorescence, old adhesive residues and any other foreign matter. cleaning may be accomplished via mechanical sanding, scraping, or chipping.
- Roughen smooth steel troweled concrete floors to ensure a good bond. It is advisable to dampen dry porous concrete before installing marbles/Tiles with ACF GRANITE AND POOL mortar. Do not leave puddles or standing water on surfaces.
- Ensure that temperatures ranges between 4 °C – 38 °C .
- Expansion joints shall be installed in accordance with local building codes. Expansion joints, control joints and cold joints shall never be bridged with setting material.
- Add **ACF GRANITE AND POOL** to clean, potable water in the ratio of 4 - 5 : 1 by weight. Mix thoroughly until smooth mortar consistency is achieved.
- If a mechanical mixer is used, do not use a high speed drill to mix mortar. Mix only enough mortar that can be used within 30 minutes. The proper mortar consistency is such that when applied with a notched trowel to the substrate, the ridges formed in the mortar will not flow or slump. Some stiffening of the mortar may occur prior to 30 minutes; re-stir occasionally. If after 30 minutes the material becomes hardened, do not add water, but discard the material.
- Spread mortar with flat side of trowel to key-in substrate; then, apply additional mortar to a depth sufficient to be notched with a suitable trowel that will leave only enough mortar to give 100% contact with back of tile and a subsequent mortar bed of 2.4mm to 4.8mm.
- With high lug tiles, “back buttering” may be required to ensure 100% coverage to back of tiles.
- During the setting of tile, it is advisable to occasionally remove a tile, to ensure good transfer of mortar to tile and for proper alignment. Do not adjust tiles in mortar after they have been set past 10-15 minutes.

NOTE: As a practical test it is recommended that three or more separate 30cm² areas of tile be bonded to the properly prepared surface with the actual tile and bonding material that will be used on the finished installation. These should be allowed to cure for 24 hours and then removed with a hammer and chisel. At this point, one can determine if adequate bond has been obtained or if a problem exists.

Limitation

- **ACF GRANITE AND POOL** must not be applied directly over wood, asphalt sheeting, vinyl covered wall board, cement asbestos board, metal, glass, plastic, or gypsum mortar beds.
- Apply in temperature ranges above 4 °C (Do not allow mortar to freeze for the first 72 hours). Lower temperatures may require longer set time before traffic is allowed.

Cleaning & Maintenance

Water is all that is needed to remove uncured mortar.



Health & Safety

- Use mask, nose cover and hand gloves during application.
- Clean hands with soap water after application.
- Ensure adequate ventilation and avoid inhalation of dust.
- Avoid contact with skin / eyes. In case of unlikely contact with eyes, rinse immediately with plenty of clean water, then cleanse with soap and lukewarm water and seek medical advice. Do not use solvent to clean the contacted area.
- Prevent swallowing. In case of unlikely swallowing, seek medical attention immediately. Do not induce vomiting

Packaging

Available in 20 kg polythene bags

Storage

Store in a cool dry place under shed away from heat.

Shelf Life

12 months in original unopened sealed condition.

Note: *The initial controls of our product are made during the production phase. We guarantee the quality of our products. All recommendations and instructions on the data sheet are generally based on our experience. Please contact us for applications on special surfaces are not mentioned in the datasheet. Our company reserves the right to update the information on the data sheet in case of technical needs without notice.*

ALAZIZYA Chemicals Factory
PO Box: -21898, Street 1, New Industrial Area
Doha –Qatar
Telephone: - +97444110552
Fax. No: -
www.alazizyachemicals.com